



HAL
open science

Using Raman Microscopy to Study the Structure of Airplane Soot and Surrogates

I.K. Ortega, B. Chazallon, Y. Carpentier, A. Bescond, Jérôme Yon, D.
Delhaye, D. Gaffié, C. Focsa

► **To cite this version:**

I.K. Ortega, B. Chazallon, Y. Carpentier, A. Bescond, Jérôme Yon, et al.. Using Raman Microscopy to Study the Structure of Airplane Soot and Surrogates. International Aerosol Conference 2014, Aug 2014, BUSAN, South Korea. hal-01071672

HAL Id: hal-01071672

<https://onera.hal.science/hal-01071672>

Submitted on 6 Oct 2014

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Using Raman Microscopy to Study the Structure of Airplane Soot and Surrogates

I. K. Ortega^{1*}, B. Chazallon¹, Y. Carpentier¹, A. Bescond², J. Yon², D. Delhayé³, D. Gaffié³ and C. Focsa¹

¹Laboratoire de Physique des Lasers, Atomes et Molécules, Université Lille 1, 59655 Villeneuve d'Ascq, France

²UMR 6614 CORIA, Université et INSA de Rouen, Av. de l'Université, BP 8, 76801 Saint-Etienne du Rouvray, France

³Onera – The French Aerospace Lab, F-91123 Palaiseau, France

*Corresponding author: ismael.ortega@univ-lille1.fr

Keywords: Raman, soot structure, combustion aerosol, aviation

Air traffic is one of the main sources of man's impact on the atmosphere. Emission of soot particles by airplanes has a significant influence on the climate. Soot particles affect climate directly by the formation of long-lived contrails and indirectly by acting as nuclei for cirrus clouds formation. There are some experiments focused on ice nucleation on soot, yet no definitive conclusion has been reached. Most likely one of the reasons behind these discrepancies resides in the different physico-chemical properties of soot particles produced in different conditions, e.g. with respect to fuel or combustion techniques.

The aim of our work is to investigate the influence of the combustion conditions on the structure of generated soot. We have used Raman microscopy (514 and 785 nm excitation) to study the spectral parameters of the first-order Raman band of various soot samples, collected from three different sources in the frame of the MERMOSE project (<http://mermose.onera.fr/>): PowerJet SaM-146 turbofan (four engine regimes), CAST generator (propane fuel, four different global equivalence ratios), and Kerosene laboratory flame. Figure 1 shows typical Raman spectra recorded for some of these samples.




Figure 1. Raman spectra of different soot particles obtained with $\lambda_0=514$ nm excitation.

To analyze the spectra a de-convolution is performed using the approach described by Sadezky *et al.* (2005). For each sample we calculated the contributions from five different bands: G band, corresponding to ideal graphite lattice (E_{2g} symmetry), D_1 band corresponding to a disordered graphite lattice (contribution from the edges, A_{1g} symmetry), D_2 band corresponding to a

disordered graphite lattice (contribution from the surface, E_{2g} symmetry), D_3 band corresponding to amorphous carbon, and D_4 band corresponding to disordered graphite lattice (A_{1g} symmetry), polyenes or ionic impurities. Table 1 summarizes these results.

Table 1. Spectra de-convolution. Band positions (cm^{-1}), integrated areas and peak area ratios relative to G band.

Band	Parameter	CAST _A	CAST _C	Kerosene	SaM-146
G	Position	1585	1585	1585	1580
	Area	4.3×10^5	2.3×10^6	1.1×10^6	2.0×10^5
D_1	Position	1345	1350	1350	1350
	Area	9.9×10^5	2.5×10^6	7.8×10^5	3.5×10^5
	A_d/A_g	2.3	1.1	0.71	1.7
D_2	Position	1608	1608	1608	1600
	Area	1.1×10^5	1.1×10^6	1.2×10^5	1.2×10^5
	A_d/A_g	0.25	0.47	0.11	0.57
D_3	Position	1520	1510	1500	1505
	Area	1.5×10^6	5.8×10^6	2.1×10^6	4.7×10^5
	A_d/A_g	3.5	2.5	1.9	2.3
D_4	Position	1230	1280	1280	1280
	Area	8.6×10^5	5.3×10^6	1.8×10^6	3.2×10^5
	A_d/A_g	2.0	2.25	1.65	1.55

CAST_A (equivalence ratio ~ 1) and airplane soot samples exhibit similar Raman spectra. Both present an important contribution of D_1 and D_3 bands. On the other hand the contribution of D_2 band is larger in the case of airplane soot. This might indicate that the size of the graphite crystallites is smaller in the case of airplane soot. Moreover, similarity of structure can promote CAST soot as a good candidate for airplane soot surrogate, though a comparison of other physico-chemical properties, like surface chemical composition, should be performed as well to confirm this suitability. Influence of the structural and physico-chemical properties of soot particles on their potential to act as ice nuclei will be investigated in the near future.

Acknowledgments

This work was supported by the French Civil Aviation Authority (DGAC) through the MERMOSE project.

References

Sadezky, A., Muckenhuber, H., Grothe, H., Niessner, R. and Pöschl U., (2005) *Carbon*, **43**, 1731-1742.